

## **Cause and Prevention of Galvanic Corrosion in Aluminum**

### **Cause**

Four conditions must be present for galvanic corrosion to occur:

- **Cathode** - the more noble or least active metal. This metal has current discharge properties and will be protected from corrosion by the presence of the anode metal. Cathode examples: copper, gold, silver, nickel
- **Anode** - the least noble or active metal. This metal has current acceptance properties and will corrode. Anode examples: magnesium, zinc, aluminum
- **Electrolyte** - the capacity to conduct electrical current through the flow of ions. Electrolyte example: water
- **Metallic path** - metallic connection conducting electrical current.

Other factors affecting the corrosiveness of water are pH, temperature, and oxygen content. Water pH should remain between 6 and 8 to minimize corrosion. Increased temperature and oxygen in water also accelerate corrosion.

### **Prevention**

Five ways to inhibit galvanic corrosion in water systems:

- **Cathodic Protection** - A sacrificial anode (usually a zinc or magnesium rod) is installed in the system. The material is more anodic in nature than the aluminum and draws the corrosion away from the aluminum. This is a higher maintenance solution as the anode must be replaced periodically.
- **Water Condition** - Change the water treatment system. Eliminate any chlorine or floating ions and monitor the pH level of the water. Add corrosion inhibitors.
- **Material Selection** - Change the ratio of dissimilar metals so it is more evenly balanced, or remove the dissimilar metals completely. Use stainless steel components.
- **Coatings** - Insulate the metals with a protective coating. This is often temporary. The anodizing on our aluminum manifolds usually provides adequate protection, except in severe environments.
- **Metal Isolation** - Install an insulative fitting, such as a PVC bushing or pipe connection to break the electrical connection of the metallic path.

**burger &  
brown engineering, inc.**

4500 E 142nd Street • Grandview MO 64030

tel 816-878-6675 • fax 816-878-6683

[www.smartflow-usa.com](http://www.smartflow-usa.com)

This information is provided solely as a service to our customers, and in no way infers any liability on the part of Burger & Brown Engineering, Inc, its representatives, or distributors.

form 138 (10.06)